



HEGGEL® SP 664

Halogen-Free Sodium Silicate Mortar

You Build, We Protect!

Description: **HEGGEL SP 664** is a halogen-free Sodium Silicate mortar, which in order to be applied only needs to be mixed with water; which chemically reacts with the powder to harden. The Hardener and Binder are included in the powder.

- Characteristics:**
- Halogen-Free, containing no fluorides
 - Extreme high corrosion protection
 - Temperature Resistance to +900°C
 - Easy to use

Applications: **HEGGEL SP 664** is used mainly for the fixing of Electrodes in Halogen Lamps. It is also used as an insulator in the electronics industry. **HEGGEL SP 664** has relatively good water and rinsing properties, but does not allow for permanent operation. With the exception of Hydrofluoric Acid, **HEGGEL SP 664** is resistant to all acids, solvents, oxidising agents, oils and fats; but is not resistant to alkalis.

Chemical Resistance: Information on the chemical resistance properties is available on request or can be taken from the resistance chart.

Substrate: Suitable substrates are ceramic, glass or metal substrates. Components shall be designed and manufactured in accordance with EN 14879-1.

Pot Life (20°C):

Product	Time
HEGGEL SP 664	Approx. 90 min

Curing (20°C):

Load Capacity	Time
Loadable	24 hrs

Packaging: The products are supplied in the following standard package sizes:

Product	Size
HEGGEL SP 664 Powder	25 kg

Storage: The materials must be stored at a cool and dry place, protected from direct sunlight. At the specified storage temperatures, the minimum shelf life of the products is given for the following periods:

Product	Temperature	Shelf Life
HEGGEL SP 664 Powder	-	24 Months

If the storage time is exceeded, the materials must be tested before use. Higher storage and transport temperatures will reduce the shelf life. The containers must be kept tightly closed. Liquid products must be stored frost-proof.

1. Surface Preparation

1.1. Carbon Steel

All contaminants, including non-visible detectable contaminants, must be removed in accordance with DIN Fachbericht # 28 and EN ISO 8502.

Ferretic steel surfaces shall be abrasive blasted to "Near White Metal". A standard preparation degree of SA 2½ according to EN ISO 12944-4 must be achieved.

1.2. Ceramic and Glass

Appropriate action shall be taken to prepare the surfaces; dry and free of dust and free of contaminants such as oil or grease and shall have minimum peel strength of 1.5 N/mm². A mechanical treatment by blasting may be required.

2. Environmental Conditions

Environmental Conditions	Value
Relative Humidity	≤ 80%
Surface Temperature	≥ +10°C up to +30°C
Application Temperature	+20°C ± 5°C recommended
Dew Point Distance	min 3°C

3. Application

Lamps which have been jointing or filled with **HEGGEL SP 664** can only be put into operation, after the mortar has completely hardened.

4. Application Tools

The following equipment is essential for the application of **HEGGEL SP 664**:

- Stirrer (max 300 rpm)
- Measuring Jugs and Mixing vessels
- Brushes
- Mortar Trowel
- Jointing Trowel, Joint Extruder
- PSA (safety glasses, rubber gloves etc.)

5. Mixing Ratio

Pour the water into a mixing tub. Add the **HEGGEL SP 664 Powder** mixing constantly and thoroughly (3 min) until a homogenous and lump-free mass is produced.

When mixing **HEGGEL SP 664**, a characteristic is that mixture is an often found to be too dry at first; although after 5 min of mixing, a mix is produced which is

good to apply. At lower temperatures, warmed water (+30°C to +60°C) could be used to shorten the mixing time

HEGGEL SP 664	kg	Parts per weight	Parts per volume
Water	0.28	18	-
HEGGEL SP 664 Powder	1.55	100	-
1.83 kg = 1 Litre			

6. Cleaning

Clean all equipment immediately after use with water. The cleaning is to be carried out as long as the material is not cured.

7. Safety Measures

The material safety data sheets of the individual components, the safety instructions on the packing (label) as well as the legal requirements for handling hazardous materials must be observed.

Technical Data

Title	Standard	Value	Unit
Flexural Strength	DIN EN ISO 178	8	N/mm ²
Density (completed mixture)	DIN EN ISO 2811-1	1.83	g/cm ³
Compressive Strength (Cylinder)	DIN EN ISO 604	20	N/mm ²
Modulus of Elasticity	-	1.1 x 10 ⁴	N/mm ²
Hardness Shore D	-	> 30	-
Lineal Co-efficient of Expansion	-	12 x 10 ⁻⁶	K ⁻¹
Max. Operating Temperature	-	+900	°C
Thermal Conductivity	-	1.2	W/m.K

HEGGEL SP 664; Revision No: 1.10 / Last Revision Date: 20.07.2023

All information contained herein is based on the current state of our knowledge and practical experience at the time of release. Therefore, please make sure that this is the latest edition of the Technical Data Sheet. All data are only intended as a guideline for informational purposes and do not constitute a legally-binding warranty of the suitability for a certain purpose of use, due to its dependence on site conditions and possible processing, use and applications. All information contained in this technical datasheet is subject to change without notice.

HEGGEL GmbH

Huttropstr. 60
45138 Essen
Germany

Tel: +49 201 17003 270

Fax: +49 201 17003 277

E-Mail: info@heggel.de

Web: www.heggel.de